


adiation-resistant fibers (PANDA)



Specifications

Attenuation coefficient at wavelength 1550, nm **1.77 dB/km**

Attenuation coefficient at wavelength 1300, nm **1.47 dB/km**

Numerical aperture of the core **0.14**

H-parameter in transport coil **$1.26 \times 10^{-3} \text{ m}^{-1}$**

Diameter, mm **88/168 μm**

Operating wavelength, nm **1350**