adiation-resistant fibers (PANDA)



cifications

Attenuation coefficient at wave length 1550, nm	1.77 dB/km
Attenuation coefficient at wave length 1300, nm	1.47 dB/km
Numerical aperture of the core	0.14
H-parameter in transport coil	1.26 x 10–3 m-1
Diameter, mm	88/168 µm
erating wavelength, nm	1350